

EVERCOAT®

INNOVATIVE SOLUTIONS
THAT PERFORM.

POLY-FLEX™



Flexible Polyester Glazing Putty

+

Extreme flexibility

The very latest filler technology

Excellent adhesion thanks to ZNX-7 technology

Self-levelling

Easy sanding

Even, smooth, pin-hole free finish

POLY-FLEX is a highly flexible polyester glazing putty for the repair of plastics.

The product has been developed to give the maximum amount of flexibility when repairing bumpers and other flexible plastic parts with exceptional adhesion characteristics.

Due to the low viscosity and self-levelling features it is easy to achieve an even, smooth, fine, pin-hole free surface.

POLY-FLEX can be used on all hard, flexible and composite plastics including SMC and polyester filler.

POLY-FLEX™
104411 – 880 ml

*Test it yourself and
experience the many
advantages it brings to
your repair process!*

TECHNICAL DATA SHEET

EVERCOAT®

POLY-FLEX™

Highly Flexible Polyester glazing putty

Edition: SP04.00565 - Rev.01 | Page 1/2

DESCRIPTION AND APPLICATION	FOR PROFESSIONAL USE ONLY Highly flexible polyester glazing putty for the filling and finishing of small damages, heavy sand scratches and micro-pin holes on plastic parts.																
SUBSTRATES	Exceptional adhesion to a variety of suitably abraded substrates including; hard plastics, flexible plastics, composite plastics, hard plastics, SMC, polyester filler. ATTENTION: When using on TPO (thermo-plastics such as PP) maintain as much of the original material as possible and oxidise the surface using a flame.																
PREPARATION	Before sanding, thoroughly clean the area to be repaired removing all traces of dirt, oil and wax residues. Lightly abrade the repair area to key the surface P80-P180. Use a fine abrasive to remove any deep or heavy scratch pattern P180-P220. Remove the dust. The area to be repaired must be completely dry before application of product.																
MIXING	The mixing ratio is 2% by weight. Place the required amount of material on a clean, grease free, mixing board and add the requisite 2% hardener. Refer to the illustration on the product lid for an optical guide to ensuring the correct ratio. Thoroughly mix the material to a consistent, homogeneous mass that is one uniform colour. Only use the EVERCOAT hardener provided.																
APPLICATION	First, apply a very thin layer of mixed material with firm pressure to the repair area. This promotes an optimum, pin-hole free application and excellent adhesion. Increase to the desired depth of repair by applying layers of product.																
FINISHING	After 20-25 minutes the sanding process can begin. The initial sanding can begin with P180 – P320 grit, avoiding deep sand scratches outside of the repair area.																
TECHNICAL DATA	<table border="1"><tr><td>Color</td><td>Light grey</td></tr><tr><td>Physical state</td><td>Liquid</td></tr><tr><td>Solubility</td><td>Not soluble in cold and warm water</td></tr><tr><td>Working time</td><td>5-6 minutes</td></tr><tr><td>Dry to sand time</td><td>20-25 minutes</td></tr><tr><td>Maximum build</td><td>3 mm (sanded)</td></tr><tr><td>Ingredients and Precautions</td><td>Safety data sheet (MSDS) available on request</td></tr><tr><td>VOC</td><td>EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC</td></tr></table> <p>The properties are typical values and not to be considered as technical sales specifications. The physical test was at about 25 °C and 75 % relative humidity unless otherwise specified.</p>	Color	Light grey	Physical state	Liquid	Solubility	Not soluble in cold and warm water	Working time	5-6 minutes	Dry to sand time	20-25 minutes	Maximum build	3 mm (sanded)	Ingredients and Precautions	Safety data sheet (MSDS) available on request	VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC
Color	Light grey																
Physical state	Liquid																
Solubility	Not soluble in cold and warm water																
Working time	5-6 minutes																
Dry to sand time	20-25 minutes																
Maximum build	3 mm (sanded)																
Ingredients and Precautions	Safety data sheet (MSDS) available on request																
VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC																
STABILITY	Best before date: 18 month from manufacturing date The manufacturing date is within the batch-identification number on the bottom of the can or on the label. The batch-identification is composed as follow: 24 10 001320 24 = year 2024 10 = month October 001320 = running batch number																
STORAGE	According to the requirements of local regulations. Observe the precautionary statements given on the label. Maximum storage temperature 25 ° C. Store in a cool, well-ventilated place away from incompatible materials and sources of ignition. Keep away from oxidising agents, strong alkalis and acids. Smoking is prohibited in the immediate vicinity. Prevent unauthorized access. Opened containers should be closed carefully and tightly. Keep upright to prevent leakage. Do not empty into drains. Do not return mixed material to the original container.																
SAFETY INSTRUCTIONS	Be sure to read all instructions and warnings before using EVERCOAT products. Safety data sheets for all materials are available online at https://itwevercoat-sds.thewerco.com/ .																

EVERCOAT®



INDASA

Official distributor
partner for Europe

Your EVERCOAT partner:

INDASA - INDÚSTRIA DE ABRASIVOS, S.A.

Apartado 3005
3801-101 Aveiro, Portugal
Tel. +(351) 234 303 600
Fax +(351) 234 303 605
E-mail: indasa@indasa.pt