

EVERCOAT®

INNOVATIVE SOLUTIONS
THAT PERFORM.

METAL GLAZE® ULTRA



**METAL GLAZE ULTRA is the
world's best sanding
polyester putty**



+

**Can be applied directly to sanded OEM clearcoat
for small repairs**

Spreads smoothly

Self leveling

Contains *ECORESIN™*

METAL GLAZE ULTRA is the world's best sanding polyester putty for use as a finishing coat over body filler, large panels, or small spot filling. Its unparalleled sanding qualities are a result of the patented *ECORESIN™*. Formulated with ZNX-7 for improved adhesion.

METAL GLAZE® ULTRA
104425 – 880ml

*Test it yourself and
experience the many
advantages it brings to
your repair process!*

TECHNICAL DATA SHEET

EVERCOAT®

METAL GLAZE® ULTRA

METAL GLAZE ULTRA is the world's best sanding polyester putty

Edition: SP04.00559 - Rev.01 | Page 1/2

DESCRIPTION AND APPLICATION	FOR PROFESSIONAL USE ONLY METAL GLAZE ULTRA is the world's best sanding polyester putty for use as a finishing coat over body filler, large panels, or small spot filling. Its unparalleled sanding qualities are a result of the patent pending ECORESIN. Formulated with ZNX-7 for improved adhesion. A self-leveling finishing putty offering superior adhesion and easy sanding. Use for light filling and repair of damaged panels up to 3 mm in depth.																		
SUBSTRATES	It can be used over bare steel, galvanized and other zinc coated steel, SMC, fiberglass and aluminum, sanded body filler, sanded OEM paint, E-Coat, and cured sanded 2K primer. It can also be used for cosmetic fiberglass and composite repair.																		
PREPARATION	Clean and degrease the entire repair area with soap and water, followed by a mild degreasing solvent. Use P80-P180 to remove, or if not damaged just scuff the paint and featheredge P180-P220.																		
MIXING	Use only with the Cream Hardener supplied! Measure hardener 2% by weight (approximately a ribbon of cream hardener from edge to edge across the center of a 10 cm diameter puddle). Puddles larger than 10 cm in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.																		
APPLICATION	Apply in thin layers and spread smoothly. The unique formula will allow sanding without clogging during the curing process after appx. 10 mins. Allow to cure fully before finishing to a feather edge.																		
SANDING / FINISHING	Contour with P180 grit sandpaper. Final sand with P320 grit followed by finer grit if desired. Avoid coarse sand scratches outside the repair area during the initial cut.																		
TECHNICAL DATA	<table border="1"><tr><td>Color</td><td>Light Green</td></tr><tr><td>Physical state</td><td>Liquid</td></tr><tr><td>Solubility</td><td>Not soluble in cold and warm water</td></tr><tr><td>Working time</td><td>2.5 - 4.5 minutes</td></tr><tr><td>Dry to sand time</td><td>10 - 15 minutes</td></tr><tr><td>Corrosion Protection</td><td>500 hours salt spray (Harshaw)</td></tr><tr><td>Maximum build</td><td>3 mm (sanded)</td></tr><tr><td>Ingredients and Precautions</td><td>Safety data sheet (MSDS) available on request</td></tr><tr><td>VOC</td><td>EU limit values: 250g/l. (2007) This product contains a maximum of 42 g/l VOC</td></tr></table> <p>Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 22°C at 75% RH unless otherwise noted.</p>	Color	Light Green	Physical state	Liquid	Solubility	Not soluble in cold and warm water	Working time	2.5 - 4.5 minutes	Dry to sand time	10 - 15 minutes	Corrosion Protection	500 hours salt spray (Harshaw)	Maximum build	3 mm (sanded)	Ingredients and Precautions	Safety data sheet (MSDS) available on request	VOC	EU limit values: 250g/l. (2007) This product contains a maximum of 42 g/l VOC
Color	Light Green																		
Physical state	Liquid																		
Solubility	Not soluble in cold and warm water																		
Working time	2.5 - 4.5 minutes																		
Dry to sand time	10 - 15 minutes																		
Corrosion Protection	500 hours salt spray (Harshaw)																		
Maximum build	3 mm (sanded)																		
Ingredients and Precautions	Safety data sheet (MSDS) available on request																		
VOC	EU limit values: 250g/l. (2007) This product contains a maximum of 42 g/l VOC																		
STABILITY	Best before date: 18 month from manufacturing date The manufacturing date is within the batch-identification number on the bottom of the can or on the label. The batch-identification is composed as follow: 8 10 233 8 = year 2018 10 = month Octobre 233 = running batch number																		
STORAGE	Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C. Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidising agents, strong alkalis, strong acids. No smoking. Prevent unauthorised access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.																		
SAFETY INSTRUCTIONS	Be sure to read all instructions and warnings before using EVERCOAT products. Safety data sheets for all materials are available online at https://itwevercoat-sds.thewerco.com/ .																		

EVERCOAT®



Official distributor
partner for Europe

Your EVERCOAT partner:

INDASA - INDÚSTRIA DE ABRASIVOS, S.A.

Apartado 3005
3801-101 Aveiro, Portugal
Tel. +(351) 234 303 600
Fax +(351) 234 303 605
E-mail: indasa@indasa.pt