

# EVERCOAT®

INNOVATIVE SOLUTIONS  
THAT PERFORM.

## POLY-FLEX™



### Flexible Polyester Glazing Putty

+

**Extreme flexibility**

**The very latest filler technology**

**Excellent adhesion thanks to ZNX-7 technology**

**Self-levelling**

**Easy sanding**

**Even, smooth, pin-hole free finish**

POLY-FLEX is a highly flexible polyester glazing putty for the repair of plastics.

The product has been developed to give the maximum amount of flexibility when repairing bumpers and other flexible plastic parts with exceptional adhesion characteristics.

Due to the low viscosity and self-levelling features it is easy to achieve an even, smooth, fine, pin-hole free surface.

POLY-FLEX can be used on all hard, flexible and composite plastics including SMC and polyester filler.

POLY-FLEX™  
# 104411 – 880 ml

*Test it yourself and  
experience the many  
advantages it brings to  
your repair process!*

# TECHNICAL DATA SHEET

# EVERCOAT®

## POLY-FLEX™

Highly Flexible Polyester glazing putty

Edition: SP04.00565 - Rev.01 | Page 1/2

<b>DESCRIPTION AND APPLICATION</b>	<b>FOR PROFESSIONAL USE ONLY</b> Highly flexible polyester glazing putty for the filling and finishing of small damages, heavy sand scratches and micro-pin holes on plastic parts.																
<b>SUBSTRATES</b>	Exceptional adhesion to a variety of suitably abraded substrates including; hard plastics, flexible plastics, composite plastics, hard plastics, SMC, polyester filler. ATTENTION: When using on TPO (thermo-plastics such as PP) maintain as much of the original material as possible and oxidise the surface using a flame.																
<b>PREPARATION</b>	Before sanding, thoroughly clean the area to be repaired removing all traces of dirt, oil and wax residues. Lightly abrade the repair area to key the surface P80-P180. Use a fine abrasive to remove any deep or heavy scratch pattern P180-P220. Remove the dust. The area to be repaired must be completely dry before application of product.																
<b>MIXING</b>	The mixing ratio is 2% by weight. Place the required amount of material on a clean, grease free, mixing board and add the requisite 2% hardener. Refer to the illustration on the product lid for an optical guide to ensuring the correct ratio. Thoroughly mix the material to a consistent, homogeneous mass that is one uniform colour. Only use the EVERCOAT hardener provided.																
<b>APPLICATION</b>	First, apply a very thin layer of mixed material with firm pressure to the repair area. This promotes an optimum, pin-hole free application and excellent adhesion. Increase to the desired depth of repair by applying layers of product.																
<b>FINISHING</b>	After 20-25 minutes the sanding process can begin. The initial sanding can begin with P180 – P320 grit, avoiding deep sand scratches outside of the repair area.																
<b>TECHNICAL DATA</b>	<table border="1"><tr><td><b>Color</b></td><td>Light grey</td></tr><tr><td><b>Physical state</b></td><td>Liquid</td></tr><tr><td><b>Solubility</b></td><td>Not soluble in cold and warm water</td></tr><tr><td><b>Working time</b></td><td>5-6 minutes</td></tr><tr><td><b>Dry to sand time</b></td><td>20-25 minutes</td></tr><tr><td><b>Maximum build</b></td><td>3 mm (sanded)</td></tr><tr><td><b>Ingredients and Precautions</b></td><td>Safety data sheet (MSDS) available on request</td></tr><tr><td><b>VOC</b></td><td>EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC</td></tr></table> <p>The properties are typical values and not to be considered as technical sales specifications. The physical test was at about 25 °C and 75 % relative humidity unless otherwise specified.</p>	<b>Color</b>	Light grey	<b>Physical state</b>	Liquid	<b>Solubility</b>	Not soluble in cold and warm water	<b>Working time</b>	5-6 minutes	<b>Dry to sand time</b>	20-25 minutes	<b>Maximum build</b>	3 mm (sanded)	<b>Ingredients and Precautions</b>	Safety data sheet (MSDS) available on request	<b>VOC</b>	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC
<b>Color</b>	Light grey																
<b>Physical state</b>	Liquid																
<b>Solubility</b>	Not soluble in cold and warm water																
<b>Working time</b>	5-6 minutes																
<b>Dry to sand time</b>	20-25 minutes																
<b>Maximum build</b>	3 mm (sanded)																
<b>Ingredients and Precautions</b>	Safety data sheet (MSDS) available on request																
<b>VOC</b>	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC																
<b>STABILITY</b>	<b>Best before date: 18 month from manufacturing date</b> The manufacturing date is within the batch-identification number on the bottom of the can or on the label. The batch-identification is composed as follow: 8 10 233 8 = year 2018   10 = month Octobre   233 = running batch number																
<b>STORAGE</b>	According to the requirements of local regulations. Observe the precautionary statements given on the label. Maximum storage temperature 25 ° C. Store in a cool, well-ventilated place away from incompatible materials and sources of ignition. Keep away from oxidising agents, strong alkalis and acids. Smoking is prohibited in the immediate vicinity. Prevent unauthorized access. Opened containers should be closed carefully and tightly. Keep upright to prevent leakage. Do not empty into drains. Do not return mixed material to the original container.																
<b>SAFETY INSTRUCTIONS</b>	Be sure to read all instructions and warnings before using EVERCOAT products. Safety data sheets for all materials are available online at <a href="https://itwevercoat-sds.thewerco.com/">https://itwevercoat-sds.thewerco.com/</a> .																

## EVERCOAT



Official distributor  
partner for Europe

Your EVERCOAT partner:

### INDASA - INDÚSTRIA DE ABRASIVOS, S.A.

Apartado 3005  
3801-101 Aveiro, Portugal  
Tel. +(351) 234 303 600  
Fax +(351) 234 303 605  
E-mail: [indasa@indasa.pt](mailto:indasa@indasa.pt)